

Metalwest

A NIM Company

Carbon Steel

Hot Rolled P&O	1/4"-14 gauge
Laser Plate	1/4", 3/8", 1/2"
Cold Rolled	10 - 24 gauge
Galvanized	10 gauge - .012"
Electro-Galvanized	14 - 24 gauge
Galvannealed	11 - 24 gauge
GalXC /G30	14 - 20 gauge

Processing Capabilities

- Slitting
- Leveling/Cut-to-length
- Shearing
- Blanking
- Value-Added Services

Kynar 500® & SMP	Prepainted Galvanized
High Reflective White	Prepainted Cold Rolled

Additional grades and sizes available upon request.

THICKNESS TOLERANCE RANGES

Carbon Steel Sheets/Hot Rolled • H.R. P. & O. • Cold Rolled • Electrogalvanized

Gauge No.	Thickness, Inches			Lbs. Per Sq. Ft.	Gauge No.	Thickness, Inches			Lbs. Per Sq. Ft.
	Dec. Equiv.	H.R. & P. & O.	C.R. E.G.			Dec. Equiv.	Tol. Range C.R.	Wt. Equiv.	
4	.2242	.2152 .2332		9.375	19	.0418	.0378 .0458	1.750	
5	.2092	.2002 .2182		8.750	20	.0359	.0329 .0389	1.500	
6	.1943	.1853 .2033		8.125	21	.0329	.0299 .0359	1.375	
7	.1793	.1713 .1873		7.500	22	.0299	.0269 .0329	1.250	
8	.1644	.1564 .1724		6.875	23	.0269	.0239 .0299	1.125	
9	.1495	.1415 .1575		6.250	24	.0239	.0209 .0269	1.000	
10	.1345	.1265 .1425	.1285 .1405	5.625	25	.0209	.0179 .0239	0.875	
11	.1196	.1116 .1276	.1136 .1256	5.000	26	.0179	.0159 .0199	0.750	
12	.1046	.0966 .1126	.0986 .1106	4.375	27	.0164	.0144 .0184	0.688	
13	.0897	.0827 .0967	.0847 .0947	3.750	28	.0149	.0129 .0169	0.625	
14	.0747	.0677 .0817	.0697 .0797	3.125	29	.0135	.0115 .0155	0.562	
15	.0673	.0613 .0733	.0623 .0723	2.813	30	.0120	.0110 .0130	0.500	
16	.0598	.0538 .0658	.0548 .0648	2.500					
17	.0538	.0478 .0598	.0498 .0548	2.250					
18	.0478	.0428 .0528	.0438 .0518	2.000					

THICKNESS TOLERANCE RANGES

Galvanized • Galvannealed Steel Sheets

Gauge No.	Thickness, Inches			Lbs. Per Sq. Ft.	Gauge No.	Thickness, Inches			Lbs. Per Sq. Ft.
	Dec. Equiv.	Tol. Range	Wt. Equiv.			Dec. Equiv.	Tol. Range	Wt. Equiv.	
10	.1382	.1472 .1292	5.781	21	.0366	.0366 .0406	1.531		
11	.1233	.1323 .1143	5.156	22	.0336	.0296 .0376	1.406		
12	.1084	.1174 .0994	4.531	23	.0306	.0266 .0346	1.281		
13	.0934	.1014 .0854	3.906	24	.0276	.0236 .0316	1.156		
14	.0785	.0865 .0705	3.281	25	.0247	.0217 .0287	1.031		
16	.0635	.0695 .0575	2.656	26	.0217	.0187 .0247	0.906		
17	.0575	.0625 .0525	2.406	27	.0202	.0172 .0323	0.844		
18	.0516	.0566 .0466	2.156	28	.0187	.0157 .0217	0.781		
19	.0456	.0506 .0406	1.906	29	.0172	.0142 .0202	0.719		
20	.0396	.0436 .0356	1.656	30	.0157	.0127 .0187	0.656		

STOCKED BLANKS

COLD ROLLED MATTE FINISH

11ga	48x35.4375	48x42	48x40	
	48x40.125	48x48	48x114	
12ga	36x40	48x24	48x30	48x40
13ga	48x24	48x30	48x40	
14ga	48x24	48x30	48x36	
	48x40	48x48	48x60	
16ga	36x30	48x24	48x30	48x36
	48x40	48x48	48x60	
18ga	36x40	48x24	48x27.25	48x30
	48x36	48x40	48x48	48x50
20ga	37x30	37x37	37x50	37x71.25
	40x49	40x97	40x147	48x24
	48x30	48x36	48x40	48x48
	48x49	48x50	48x52	48x100
22ga	48x50	48x75		
24ga	48x49			
GALVANNEALED CSB NONCHEM TREAT DRY-A40*				
14ga	48x40			
16ga	48x24	48x40		
18ga	48x40			
20ga	48x40			

*A60 available upon request.

Contact your local office today!

Brighton, CO
1229 S. Fulton Ave.
Brighton, CO 80601
303.654.0300

Phoenix, AZ
800.336.3365
www.metalwest.com

Albuquerque, NM
1701 Aspen NW, Unit R
Albuquerque, NM 87104
505.243.2122

Carbon Steel

Metalwest

A NIM Company

Mill Finish Aluminum
3003 H14
3105 H14
5005 H34
5052 H32

Painted Aluminum
3105
3004 H291
White over Clear
Black over White
Black over Red

Processing Capabilities
Slitting
Leveling/Cut-to-length
Shearing
Blanking
Value-Added Services

Anodized Aluminum
.040 Clear Satin Matte .040 LA Dark Bronze
.063 Clear Satin Matte .063 LA Dark Bronze

Other options available upon request.

Aluminum Tread
3003 H22 4017 H22

Additional grades and sizes available upon request.

5052 H32 STOCKED BLANKS		
.063	.080	.125
36x72	48x24	48x40
48x30	48x40	
48x36		
48x40		
60x30		

THICKNESS TOLERANCE RANGES					
Aluminum					
Thickness	Pounds Per Sq. Ft.		Thickness Tolerances (Plus/Minus)		
	3003-H14	5052-H32	36" Wide	48" Wide	60" Wide
.025	0.356	0.349	.0015	.0020	.0030
.032	0.456	0.447	.0020	.0025	.0035
.040	0.570	0.559	.0025	.0035	.0045
.050	0.713	0.698	.0030	.0035	.0050
.063	0.898	0.880	.0030	.0035	.0050
.080	1.140	1.117	.0035	.0045	.0060
.090	1.283	1.257	.0035	.0045	.0060
.100	1.426	1.397	.0045	.0060	.0070
.125	1.782	1.746	.0045	.0060	.0070
.190	2.709	2.654	.0070	.0090	.0110
.250	3.564	3.492	.0120	.0140	.0150

Stainless 2B Finish
201 304/304L
301 316/316L
430

Stainless Polished
201
301
304 #4, #8
316
430

THICKNESS TOLERANCE RANGES				
Stainless Steel				
Gauge No.	Decimal Equivalent	Tolerance Plus/Minus	Pounds Per Sq. Ft.	
			300 Series	400 Series
7	.1875	.0070	7.90	7.76
8	.1650	.0070	6.93	6.81
10	.1350	.0050	5.67	5.57
11	.1200	.0050	5.04	4.95
12	.1050	.0040	4.41	4.33
13	.0900	.0040	3.78	3.71
14	.0750	.0030	3.15	3.09
16	.0600	.0030	2.52	2.48
18	.0480	.0030	2.02	1.98
19	.0420	.0025	1.76	1.73
20	.0360	.0020	1.51	1.49
22	.0300	.0020	1.26	1.24
24	.0240	.0020	1.01	.990
26	.0180	.0015	.756	.743
28	.0150	.0010	.630	.619

Contact your local office today!

Brighton, CO
1229 S. Fulton Ave.
Brighton, CO 80601
303.654.0300

Phoenix, AZ
800.336.3365
www.metalwest.com

Albuquerque, NM
1701 Aspen NW, Unit R
Albuquerque, NM 87104
505.243.2122

Non-Ferrous